#### Description

Polymeric PVC film, available in different colours with a glossy surface, additionally in matt white and matt black.

## **Release Paper**

Silicone coated paper on one side, 137 g/m<sup>2</sup>, which provides excellent weed-stripping properties. For white vinyl, a light blue silicone paper is used to form a stronger contrast to lettering.

#### Adhesive

Solvent polyacrylate, permanent

#### Area of use

PVC film with optimal cutting and conversion properties. Developed specially for lettering, marking and decoration. Particularly suitable for high-quality vehicle and public transport system advertising. Also suitable for uneven and slightly curved surfaces. For more curved surfaces or surfaces with corrugations or rivets, these films should be worked in, cut and applied with an overlap at the edges. The glossy surface is suitable for thermal transfer printing (with resin ribbons).

#### **Certificates**

General Type Approval (ABG) acc. to § 22a StVZO, Federal German Road Traffic Licensing Order (~~~D5291)

### **Technical Data**

Thickness* (without protective paper and adhesive)	70 micron
Dimensional stability (FINAT TM 14)	Adhered to steel, no measurable shrinkage in cross direction in length 0,2 mm max.
Temperature resistance***	Adhered to aluminium, -50° C to +90° C (short-term, max. 24h, at +100° C) no variation
Sea water resistance (DIN EN ISO 9227)	Adhered to aluminium, after 100h/35° C, no variation
Resistance to solvents and chemicals	At room temperature, 72h after adhesion to aluminium, short- term resistant to most oils and greases, fuels, aliphatic solvents, weak acids, salts and alkalis
Fire behavior (DIN 75200)	Adhered to steel, self-extinguishing
Adhesive power* (FINAT TM 1, after 24h, stainless steel)	18 N/25 mm
Tensile strength (DIN EN ISO 527)	Along: min. 19 MPa Across: min. 19 MPa
Elongation at break (DIN EN ISO 527)	Along: min. 150% Across: min. 170%
Shelf life**	2 years
Application temperature	> +8° C
Service life by specialist application Under vertical outdoor exposure (normal climate of Central Europe)	Black / white:8 yearsTransparent / Coloured:7 yearsMetallic:4 yearsBrilliant blue L:3 years

\* average \*\* in original packaging, at 20° C and 50% relative humidity \*\*\* normal climate of Central Europe



# ORACAL<sup>®</sup> 551 High Performance Cal

#### Note

The above information is based upon our present knowledge and practical experience. The information is given without any guarantee or agreement with regards to the quality or properties of the material. It does not constitute a warranty of any certain quality, properties and/or service life concerning the ORAFOL<sup>®</sup> colour films.

Please note that by nature, films are more sensitive than lacquers. Therefore films must be treated and maintained with the greatest care. For application of the ORAFOL colour films (wrapping and removal) as well as for maintenance and use, please refer to our documents 'Processing Guidelines' and 'Maintenance and Usage Terms' (both documents are available for pdf download: **www.orafol.com/gp/europe/en/support**). If our guidelines are not followed, please be advised that in particular the maximum service life information, stated as based on our experience, does not apply. Further information about the expected maximum service life is found in the Processing Guidelines (see no. 2 there). If the Processing Guidelines and Maintenance and Usage Terms are not complied with, any warranty and liability is excluded.

Please contact a professional workshop or ORAFOL's customer support if you have further questions. The batch traceability according to ISO 9001 is done on the base of the roll number.

# **IMPORTANT NOTICE**

All ORACAL<sup>®</sup> products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL<sup>®</sup> products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL<sup>®</sup> products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice. ORACAL<sup>®</sup> is a registered trademark of ORAFOL Europe GmbH

